

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : SIL 60 DURO RED

COMPOUND NO: S6001R

Physical Properties (Press Cure:170°CX10min Post Cure:200°CX4h)	Requirement	Test result
Hardness, Point 硬度(邵A)	55.00-65.00	63.00
Tensile Strength, min, Mpa 拉力強度	6.00	7.20
Ultimate Elongation, min, % 延伸率	200.00	254.00
Specific Gravity, 比重		1.21
Heat Resistance 70h@225°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	+10.00	-2.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	-4.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-45	-31.00
Compression Set 22h@175°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	25.00	13.00
Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗		
Change in hardness, Point 硬度變化	-15.00-0.00	-7.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	+0.00
Change in ultimate elongation, max, % 延伸率變化率	-20.00	+0.00
Change in volume, % 體積變化率	0.00-10.00	+7.00
Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗		
Change in hardness, Point 硬度變化	-30.00	-17.00
Change in volume, % 體積變化率	+60.00	+42.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
 THIS COMPOUND S6001R CAN MEET ASTM 2000 M5GE606A19B37EO16EO36

