

The Manufacturer of Sealing Parts

## TEST REPORT

MATERIAL : NBR 70 DURO PRO CURED BLACK

COMPOUND NO: N7021B

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h)	Requirement	Test result
Hardness, Point 硬度(邵A)	65.00~75.00	74.00
Tensile Strength, min, Mpa 拉力強度	10.00	16.30
Ultimate Elongation, min, % 延伸率	250.00	351.00
Specific Gravity, 比重		1.23
<b>Heat Resistance 70h@125°C 老化試驗</b>		
Change in hardness, max, Point 硬度變化(邵A)	0.00~15.00	+8.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	+1.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-50.00	-40.00
<b>Compression Set 22h@100°C 壓縮永久變形試驗</b>		
Compression set, Method B, max, % 壓縮永久變形	25.00	10.00
<b>Fluid Resistance No.1 Oil Resistance 70h@125°C 1號油試驗</b>		
Change in hardness, Point 硬度變化	0.00~10.00	+9.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	+4.00
Change in ultimate elongation, max, % 延伸率變化率	-35.00	-26.00
Change in volume, % 體積變化率	-15.00~5.00	-13.00
<b>Fluid Resistance No.3 Oil Resistance 70h@125°C 3號油試驗</b>		
Change in hardness, Point 硬度變化	±10.00	+1.00
Change in tensile strength, max, % 拉力強度變化率	-15.00	-9.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	-27.00
Change in volume, % 體積變化率	0.00~25.00	+1.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY  
 THIS COMPOUND N7021B CAN MEET ASTM 2000 M2CH710A25B14EQ15EO35

