

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : FKM 75 DURO FDA WHITE

COMPOUND NO: V7511W

Physical Properties (Press Cure:170°CX10min Post Cure:230°CX24h)	Requirement	Test result
Hardness, Point 硬度(邵A)	70~80	77.00
Tensile Strength, min, Mpa 拉力強度	7.00	11.70
Ultimate Elongation, min, % 延伸率	150.00	182.00
Specific Gravity, 比重		2.08
Heat Resistance 70h@250°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	+10.00	+3.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	+9.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-25.00	-12.00
Compression Set 22h@175°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	50.00	6.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
 THIS COMPOUND V7511W CAN MEET ASTM 2000 M2HK807A1-10B37

