

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : SIL 40 DURO RED

COMPOUND NO: S4001R

Physical Properties (Press Cure:170°CX10min Post Cure:200°CX4h)	Requirement	Test result
Hardness, Point 硬度(邵A)	35.00-45.00	42.00
Tensile Strength, min, Mpa 拉力強度	5.00	7.00
Ultimate Elongation, min, % 延伸率	300.00	386.00
Specific Gravity, 比重		1.12
Heat Resistance 70h@225°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	+10.00	-4.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	-3.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-30.00	+8.00
Compression Set 22h@175°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	25.00	12.00
Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗		
Change in hardness, Point 硬度變化	-10.00-0.00	-9.00
Change in tensile strength, max, % 拉力強度變化率	-30.00	-13.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	-19.00
Change in volume, % 體積變化率	0.00-15.00	+9.00
Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗		
Change in hardness, Point 硬度變化		+0.00
Change in volume, % 體積變化率	+60.00	+56.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND S4001R CAN MEET ASTM 2000 M2GE405A19B37EO16EO36

