

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : EP 70 DURO RED

COMPOUND NO: E7001R

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h)	Requirement	Test result
Hardness, Point 硬度(邵A)	65.00~75.00	70.00
Tensile Strength, min, Mpa 拉力強度	8.00	8.40
Ultimate Elongation, min, % 延伸率	200.00	447.00
Specific Gravity, 比重		1.30
Heat Resistance 70h@100°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	±15.00	+2.00
Change in tensile strength, max, % 拉伸強度變化率	±30.00	-5.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-50.00	-13.00
Compression Set 22h@70°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	25.00	13.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
 THIS COMPOUND E7001R CAN MEET ASTM 2000 M8BA708A14B13

